•

PATENT COOPERATION TRE



PCT

INTERNATIONAL PRELIMINARY EXAMINATION REPORT

(PCT Article 36 and Rule 70)

Applicant's or agent's file reference M905-PCT	FOR FURTHER ACTION See Notification of Transmittal of International Preliminary Examination Report (Form PCT/IPEA/416)			
International application No.	International filing date (day/month/year) Priority date (day/month/year)			
PCT/JP2003/013732	27 October 2003 (27.10.2003) 28 October 2002 (28.10.2002)			
International Patent Classification (IPC) or n C23C 2/06	ational classification and IPC			
Applicant	NIPPON STEEL CORPORATION			
and is transmitted to the applicant a	ination report has been prepared by this International Preliminary Examining Authority coording to Article 36. sheets, including this cover sheet.			
This report is also accompan amended and are the basis for	ied by ANNEXES, i.e., sheets of the description, claims and/or drawings which have been rethis report and/or sheets containing rectifications made before this Authority (see Rule Administrative Instructions under the PCT).			
These annexes consist of a to	otal of sheets.			
3. This report contains indications rela	iting to the following items:			
I Basis of the report				
II Priority				
III Non-establishment	of opinion with regard to novelty, inventive step and industrial applicability			
IV Lack of unity of in				
Reasoned statement under Article 35(2) with regard to novelty, inventive step or industrial applicability; citations and explanations supporting such statement				
VI Certain documents	cited ,			
VII Certain defects in t	he international application			
VIII Certain observations on the international application				
Date of submission of the demand	Date of completion of this report			
26 November 2003 (26.	11.2003) 05 October 2004 (05.10.2004)			
Name and mailing address of the IPEA/JP	Authorized officer			
Facsimile No.	Telephone No.			



INTERNATIONAL PARTIES MINARY EXAMINATION REPORT

national application No.
PCT/JP2003/013732

I. Basis	of the report	
1. With	regard to the elements of the international ap	plication:*
\boxtimes	the international application as originally fil	ed
	the description:	
	pages	
	pages	, filed with the demand
	pages	, filed with the letter of
	the claims:	
	pages	, as originally filed
	pages	, as amended (together with any statement under Article 19
	pages	, filed with the demand
	pages	, filed with the letter of
	the drawings:	
	pages	, as originally filed
	pages	, filed with the demand
	pages	, filed with the letter of
l I t	he sequence listing part of the description:	
		, as originally filed
		, filed with the demand
		, filed with the letter of
the ir	ternational application was filed, unless other e elements were available or furnished to this	Authority in the following language which is:
l H		he purposes of international search (under Rule 23.1(b)).
	the language of publication of the internati	for the purposes of international preliminary examination (under Rule 55.2 and/
	or 55.3).	
3. With preli	regard to any nucleotide and/or amin- minary examination was carried out on the b	o acid sequence disclosed in the international application, the international asis of the sequence listing:
<u> </u>	contained in the international application is	n written form.
1 📙	filed together with the international applica	-
	furnished subsequently to this Authority in	
片	furnished subsequently to this Authority in	
	The statement that the subsequently fu international application as filed has been	rnished written sequence listing does not go beyond the disclosure in the furnished.
	The statement that the information record been furnished.	ded in computer readable form is identical to the written sequence listing has
4.	The amendments have resulted in the cano	ellation of:
	the description, pages	
	the claims, Nos.	
1	the drawings, sheets/fig	
5. 🗌	This report has been established as if (som	e of) the amendments had not been made, since they have been considered to go in the Supplemental Box (Rule 70.2(c)).**
in th and	is report as "originally filed" and are n 70.17).	to the receiving Office in response to an invitation under Article 14 are referred to of annexed to this report since they do not contain amendments (Rule 70.16 and must be referred to under item 1 and annexed to this report.

V. Reasoned statement under Article 35(2) with regard to novelty, inventive step or industrial applicability; citations and explanations supporting such statement				
1. Statement				
Novelty (N)	Claim	9	YES	
	Claims	1-8	NO	
Inventive step (IS)	Claims		YES	
	Claims	1-9	NO	
Industrial applicability (IA)	Claims	1-9	YES	
	Claims		NO	

2. Citations and explanations

Document 1: WO, 98/26103, A1 (Nishin Steel Co., Ltd.)

June 18, 1998 (06.18.98), Claims, Page 9, Lines 3-5

Document 2: JP, 2002-187234, A (Nishin Steel Co., Ltd.)

July 2, 2002 (07.02.02), Claims, Page 3, Right column, Lines 22-28

Document 3: Nihon Kinzoku Gakkai Hen, Kaitei 3 Han Kinzoku Data Book, Maruzen Hakko, 1993,

p. 598, Fig. 3-625

The inventions relating to claims 1 and 5-8 are described in document 1 cited in the ISR (Claims, Column 9, Lines 3-5), and do not appear to be novel or involve an inventive step.

The applicant, in a written response dated May 25, 2004, asserts that no formation occurs of a dendrite crystal of an A1 phase with a particular size caused by a Ti-Al based intermetallic compound in a composition to which Ti and B have been concurrently added. However, the present invention, as described in page 11, permits inevitable impurities of 0.5wt% or less, including B, to be contained.

Therefore, it is found that the containing of TiAl₃ with respect to a particular phase and the formation of a dendrite crystal of an AI phase with a particular size caused thereby could be obtained based on the composition described in document 1.

The inventions relating to claims 1-8 are described in document 2 cited in the ISR (page 3, right column, lines 22-28), and do not appear to be novel or involve an inventive step.

As mentioned above, the present invention permits inevitable impurities of 0.5wt% or less including B to be contained, and in cited document 2, each of Ti and B separately suppresses Zn₁₁Mg₂ and further denies deposition of Ti-B; therefore, Ti and B do not cause a synergistic effect through compound addition thereof, and the invention includes cases where only Ti is added.

Therefore, it is recognized that the presence of an Mg₂Si phase, the containing of a Ti (Al_I-xSix)₃ with respect to a particular phase and the formation of a dendrite crystal of an A1 phase with a particular size caused thereby could be obtained based on the composition described in document 2.

The invention relating to claim 9 could be easily conceived based on the description of documents 1-3 cited in the ISR and does not appear to involve an inventive step.

As mentioned above, the present invention permits inevitable impurities of 0.5wt% or less including B to be contained and the equilibrium reaction asserted in the written response does not differ from the inventions described in documents 1 and 2 having the same composition.

It is obvious that in the technologies of documents 1 and 2 relating to hot dipping, a low melting point of a material to be melted is desirable from the standpoint of bath uniformity and energy costs; therefore, adopting a Ti-Zn based intermetallic compound that has a low melting point as a Ti material based on the description of document 3 (p.598, Figs. 3-625) would be easy for a party skilled in the art.

Regul Put/PT



特 許 協 力 条 糸



国際予備審査報告

(法第12条、法施行規則第56条) [PCT36条及びPCT規則70]

	854	
REC'D	2 1 OCT	2004
WIP	0	PCT

出願人又は代理人 の沓類記号 M905-PCT	今後の手続きについては、国際予備審査報告の送付通知(様式PCT/ IPEA/416)を参照すること。				
国際出願番号 PCT/JP03/13732	国際出願日 (日.月.年) 27.1	0.2003	優先日 (日.月.年)	28. 10.	2002
国際特許分類 (IPC) Int. Cl' C 2 3	C 2/06				
出願人(氏名又は名称) 新日本製鐵株式会	社 ————————————————————————————————————				
国際予備審査機関が作成したこの この国際予備審査報告は、この表 この国際予備審査報告には、 査機関に対してした訂正を含	紙を含めて全部で	3 ペー なれて、この報告の	ジからなる。 基礎とされた及	び/又はこ	·
全機関に対してした訂正を占 (PCT規則70.16及びPCT この附属書類は、全部で	r 実施細則第607号を ページである 	飛)			
I × 国際予備審査報告の基础	Ä				
IV 開発明の単一性の欠如	業上の利用可能性につい				ن بالد نوب باز و و مواید .
V × PCT35条(2)に規定 の文献及び説明 VI ある種の引用文献	<u>:</u> する新規性、進歩性又	は産業上の利用可能	1性についての!	見解、それを	∶ 表付りるため
VII 国際出願の不備 . VII 国際出願に対する意見					
		•			
国際予備審査の請求書を受理した日		国際予備審査報告	を作成した日		

 国際予備審査の請求書を受理した日 26.11.2003
 国際予備審査報告を作成した日 05.10.2004

 名称及びあて先 日本国特許庁(IPEA/JP) 郵便番号100-8915 東京都千代田区設が関三丁目4番3号
 特許庁審査官(権限のある職員)
 4E 3134

 小柳 健悟
 電話番号 03-3581-1101 内線 3423

国际 1 個角電水口	
国際予備審査報告の基礎	
. この国際予備審査報告は下記の出願咨類に基づいて作成され 応答するために提出された差し替え用紙は、この報告書によ PCT規則70.16,70.17)	いた。(法第6条(PCT14条)の規定に基づく命令に SNVて「出願時」とし、本報告書には添付しない。
× 出願時の国際出願書類	
リ 明神皆	出願時に提出されたもの 国際予備審査の請求審と共に提出されたもの
請求の範囲 第	\
図面 第 ページ/図 図面 第 ページ/図 図面 第 ページ/図	、出願時に提出されたもの 、国際予備審査の請求書と共に提出されたもの 、 付の書簡と共に提出されたもの
明細書の配列表の部分 第 ページ 明細書の配列表の部分 第 ページ 明細書の配列表の部分 第 ページ	、出願時に提出されたもの
2. 上記の出願書類の言語は、下記に示す場合を除くほか、こ	の国際出願の言語である。
上記の書類は、下記の言語である語であ	oa.
国際調査のために提出されたPCT規則23.1(b)にい PCT規則48.3(b)にいう国際公開の言語 国際予備審査のために提出されたPCT規則55.2ま 3. この国際出願は、ヌクレオチド又はアミノ酸配列を含んで	たは55.3にいう翻訳文の言語
この国際出願に含まれる書面による配列表	
この国際出願と共に提出された磁気ディスクによる 出願後に、この国際予備審査(または調査)機関に	・配列表 :提出された書面による配列表
	r 提出された磁気ディスクによる��クリネス
出願後に提出した書面による配列表が出願時におけ	ける国際出願の開示の範囲を超える事項を占まない自む時代
書の提出があった 書面による配列表に記載した配列と磁気ディスクに があった。	こよる配列表に記録した配列が同一である旨の陳述書の提出 ·
4. 補正により、下記の書類が削除された。 [] 明細書 第	ページ
明細書 第 請求の範囲 第	項
図面 図面の第	ページ/図
5. この国際予備審査報告は、補充欄に示したように、補れるので、その補正がされなかったものとして作成し記1. における判断の際に考慮しなければならず、本	前正が出願時における開示の範囲を超えてされたものと認めら √た。(PCT規則70.2(c) この補正を含む差し替え用紙は♪ ≤報告に添付する。)

v.	新規性、進歩性又は産業上の利用可能性についての法第12条 (PCT35条(2)) 文献及び説明	に定める見解、	それを娶付ける
1.	見解		

新規性(N) 請求の範囲 9 請求の範囲 1-8

進歩性(IS) 請求の範囲 有 請求の範囲 1-9

請求の範囲 1-9 産業上の利用可能性(IA) 請求の範囲

文献及び説明 (PCT規則70.7)

文献1:WO 98/26103 A1 (日新製鋼株式会社) 1998.06.18, 請求の範囲, 第9頁第3-5行

JP 2002-187234 A (日新製鋼株式会社)

2002.07.02,特許請求の範囲,第3頁右欄第22-28行 文献3:日本金属学会編,改訂3版金属データブック, 丸善発行 1993, p. 598 図3・625

請求の範囲1、5-8に係る発明は、国際調査報告で引用された文献1の特別の範囲、第9欄第3-5行に記載されているので、新規性、進歩性を有しない。 5-8に係る発明は、国際調査報告で引用された文献1の特許請求・

出願人は、2004年5月25日付答弁書において、TiとBを同時に添加した組成ではTi-A1系金属間化合物に起因する特定の大きさのA1相の樹枝状晶の形成 は起こらない旨主張するが、本願発明は、第11頁に記載されているように、Bを含む不可避的不純物を0.5質量%以下含有することを許容するものである。

特定相に対するTiAl3の含有、及びこれに起因する特定の大きさのA 1相の樹枝状晶の形成は、上記文献1に記載された組成によって得られるものと認め

請求の範囲1-8に係る発明は、国際調査報告で引用された文献2の特許請求の範 囲、第3頁右欄第22-28行に記載されているので、新規性、進歩性を有しない。 上述のように、本願発明は、Bを含む不可避的不純物を0.5質量%以下含有する ことを許容するものであり、また、引用文献2において、TiとBは、それぞれ別途 ZniMg2の抑制を図るものであり、さらに、Ti-Bの析出を否定するものであ るから、TiとBは複合添加による相乗効果を図るものではなく、Tiのみ添加する 場合も含むものである。

よって、Mg2Si相の存在、特定相に対するTi (Al1-xSix)3の含有、 これに起因する特定の大きさのAl相の樹枝状晶の形成は、上記文献2に記載された 組成によって得られるものと認める。

請求の範囲9に係る発明は、国際調査報告で引用された文献1-3の記載から容易 になし得るものであり、進歩性を有しない。

上述のように、本願発明は、Bを含む不可避的不純物を0.5質量%以下含有する とを許容するものであるから、上記答弁書で主張する平衡反応は、同じ組成を有す る上記文献1、2に記載された発明において相違するものではない。

そして、溶融めっきに関する上記文献1、2の技術において、浴の均一性、及びエネルギーコストの観点から、溶解するべき素材の融点が低いことが望ましいことは自明なことであり、文献3の記載(p. 598 図3・625)に基づいて、Ti素材 として低融点であるTi-Zn系金属間化合物を採用することは、当業者にとって容 易である。